Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-03-07-07** **Date: 10-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP,
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to footpath and providing cobble stones at Yelahanka new town 5th phase LIG block in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000124/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-07 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-03-2018
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.33	–
2	Finess by Air permeablity method (m^2/kg,Min)	265.5	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	170 minutes	Not less than 30 minutes
6	Final Setting time	260 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

AE-2

AE-02

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-03-07-07** **Date: 10-03-2018**
Customer	:	Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.
Address	:	Yelahanka Sub division, BBMP, Bangalore.
Project Name	:	Improvements to footpath and providing cobble stones at Yelahanka new town 5th phase LIG block in ward No.02 of Yelahanka Sub Division.
Agency	:	Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64
Customer's Reference	:	EE(YNK.D)E-PMT-14/W.O/000124/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	07-03-2018
Sample ID No	:	2018-03-07-07 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-03-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	244	244	1.6	98.4	90-100
3	20 mm	5344	5588	37.3	62.7	30-70
4	10 mm	4422	10010	66.7	33.3	10-35
5	4.75 mm	4733	14743	98.3	1.7	0-5
6	Pan	257	15000	100.0	0	---

AE-2

AE-02

CIVIL PRO Sig..... Date.....

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-03-20-08** **Date: 24/03/2018**

Customer : Assistant Executive Engineer, Yelahanka Sub division, BBMP, Bangalore.

Address : Yelahanka Sub division, BBMP, Bangalore.

Project Name : Improvements to footpath and providing cobble stones at Yelahanka new town 5th phase LIG block in ward No.02 of Yelahanka Sub Division.

Agency : Sri.Y.A Dhanashekar, No.10, K.H.B Colony Yelahanka, Bangalore-64

Customer's Reference : EE(YNK.D)E-PMT-14/W.O/000124/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-03-2018

Sample ID No : 2018-03-20-08 /01

Customer ID : RMC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/03/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RMC	M20	17/03/2018	24/03/2018	150.33 X 150.34 X 150.30	22601	8.243	411.3	18.2	18.2
2	RMC	M20	17/03/2018	24/03/2018	150.32 X 150.44 X 150.35	22614	8.304	418.4	18.5	
3	RMC	M20	17/03/2018	24/03/2018	150.22 X 150.24 X 150.35	22569	8.312	404.0	17.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2

AE-02

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com